





# **IGLU'** H 22 cm

#### **APPLICATIONS**

Ventilated under-floor cavities for civil and industrial buildings that are being built new or reconstructed. - Urban infrastructure structures - Creation of an intermediate slab or roofing for cavities used for ventilation and the passage of systems. - Rooms used for humidity and temperature control: drying cells, cold rooms, greenhouses, storage rooms and cellars. - Underground pipes for the passage of utilities. Inspectionable cavities and pits. - By filling it in simply with expanded clay, it can be used to create roof-top gardens. - Underground ducts for the dispersion of water and for drainage. - Overhead sidewalks for passenger loading and unloading or the creation of floating floors. -Levelling height.

Made in ALAPLEN® CS20





#### Measures are express in mm.\*

\* Recyclable material is allowed a size tolerance of ± 1,5%.

# 0,036 m<sup>3</sup>/m<sup>2</sup> Quantity of concrete to the crown\*\*

\*\* The volume may vary depending on the pouring condition and the tolerance of the material.

## **IGL(1**" H 22 cm

#### Pressures at the bottom of the structure

Loads Kg/m²	Slab cm	Mesh Ø mm cmxcm	Thickness of the lean concrete cm	Pressure at pillar base Kg/cm <sup>2</sup>
1.500	4	Ø5 / 25 X 25	5 10 15	1,49 0,71 0,43
5.000	5	Ø6 / 15 X 15	10 15 20	2,10 1,21 0,79
10.000	8	Ø8 / 20 X 20	15 20 25	2,35 1,53 1,07

The table expresses, starting from the various examples of overload and of thickness (to be given to the slab), the pressures that would be applied to the feet of the structure, in relation to the (eventual) thicknesses of the lean concrete.

The overload hypotheses indicated are normally those laid down by law; the actual load capacity is far superior.

To contact the technical office: Tel. +39 0422 208350 - tecnico@daliform.com

To obtain updated technical cards, support material, new photos and case studies, go to

www.daliform.com - The technical consultancy is only valid for the Daliform Group construction systems.

## Technical data and packing


<b>IGLU</b> <sup>4</sup> H 22 cm						
Pallet dimensions	Pallet dimensions	cm	110x110x225			
IGLU' C	Sq.mt. per pallet	m²/PAL	80			
	Pieces per pallet	pz./PAL	320			
r a r×b	Pallet weight	Kg./PAL	440			
L-Plast panels	н	cm	20			
	L	cm	205			
	Ρ	cm	15			

To contact the technical office: Tel. +39 0422 208350 - tecnico@daliform.com

To obtain updated technical cards, support material, new photos and case studies, go to www.daliform.com - The technical consultancy is only valid for the Daliform Group construction systems.

### Dry-stone time-exposure of IGLU': 80 m²/h

#### Dry assembly method



The information contained in this catalogue could be changed. Before placing an order, request a confirmation or updated information from the DALIFORM GROUP, which reserves the right to make changes at any moment without notice. In consideration of recycled material, it is specified that there are tolerance margins caused by environmental factors



Tel. +39 0422 208350 - Fax +39 0422 800234 export@daliform.com www.daliform.com Via Serenissima, 30 - 31040 Gorgo al Monticano (TV) - Italy







Certified Management System ISO 14001:2004 - ISO 9001:2008 - BS OHSAS 18001:2007

Partner of GBC Italia

